

MELBOURNE 0807

牛皮 / NATURAL LEATHER



技术指标 TECHNICAL DATASHEET	测试标准 TEST	单位等级 UNIT	认证结果 GUARANTEED
接触到香烟和火柴的可燃性 BURNING BEHAVIOUR TO CIGARETTE AND MATCH FLAME	CAL TB-117 (2013, Sec.1) BS 5852:1979 BS EN 1021-1-2:2006	 FIRE RETARDANT	通过 PASS
摩擦色牢度 干性250次 COLOUR FASTNESS TO RUBBING DRY 250 CYCLES	UNI EN ISO 11640:1998	灰度等级 GREY SCALE	>= 3
摩擦色牢度 湿磨150次 COLOUR FASTNESS TO RUBBING WET 150 CYCLES	UNI EN ISO 11640:1998	灰度等级 GREY SCALE	>= 3
摩擦色牢度 汗液20次 COLOUR FASTNESS TO RUBBING SWEAT 20 CYCLES	UNI EN ISO 11640:1998	灰度等级 GREY SCALE	>= 3
撕裂强度 单边撕裂 TEAR STRENGHT SINGLE EDGE TEAR	UNI EN ISO 3377	N	>= 20
光照色牢度 曝光能量16.000千焦耳/平方米 COLOUR FASTNESS TO ARTIFICIAL LIGHT EXPOSITION ENERGY 16.000 kj/sqm	UNI EN ISO 105 B02 (MET.5)	蓝色等级 BLUE SCALE	>= 4
原产地澳大利亚, 轻微打磨的天然纹理 轻柔的油蜡手感和半哑光外观 1.1 - 1.3 毫米 厚度 平均 4.5 平方米 AUSTRALIAN BOVINE ORIGIN, LIGHTLY BUFFED NATURAL GRAIN SOFT WAXY FEEL AND SEMI-MATTE APPEARANCE 1.1 - 1.3 mm THICKNESS 4.5 sqm AVERAGE	避免直接暴露在阳光和其他热源下。 任何脏渍，溅洒，污物都应该及时清理 用一块干净的布配上中性肥皂液以作圆周运动发方式擦拭。 对于任何以下问题造成的损坏我们不承担责任 使用不当， 化学试剂清洗或者额外注入。 AVOID EXPOSING DIRECTLY TO SUNLIGHT AND HEAT SOURCES. ANY STAIN, SPILLS OR SOILING SHOULD BE CLEANED UP PROMPTLY WITH A NEUTRAL SOAP SOLUTION USING A CLOTH IN SMOOTH CIRCULAR MOVEMENTS. WE DO NOT ACCEPT RESPONSIBILITY FOR ANY DAMAGE RESULTING FROM INAPPROPRIATE USE, CHEMICAL CLEANING OR ADDITIONAL IMPREGNATION.	24小时内发货 在线实时库存-随时发货 全球发货 24h DELIVERY TIME E-STOCK SERVICE - READY TO SHIP WORLDWIDE SHIPPING AVAILABLE	